

IC55 CONTOURS ISOCORE RIGID CLICK

TECHNICAL DATA SHEET



PHYSICAL PROPERTIES & PACKAGING RIGID CLICK FLOORING			
Collection	HERRINGBONE	CHEVRON	VERSAILLES
Use	Commercial & Residential	Commercial & Residential	Commercial & Residential
Size	120 mm (4,72") x 720 mm (28,35")	120 mm (4,72") x 690 mm (27,16")	305 mm (12,01") x 1407,8 mm (55,42")
Thickness - Overall	8,0 mm	8,0 mm	8,0 mm
Product Construction	2.0 LVT Top layer (including 0.55mm Wear Layer) 5.0 mm Isocore Core 1.0mm HDPE Acoustic Underlay	2.0 LVT Top layer (including 0.55mm Wear Layer) 5.0 mm Isocore Core 1.0mm HDPE Acoustic Underlay	2.0 LVT Top layer (including 0.55mm Wear Layer) 5.0 mm Isocore Core 1.0mm HDPE Acoustic Underlay
Wear Layer - Thickness	0.55 mm	0.55 mm	0.55 mm
Edge Detail	4 sides Micro Bevel	4 sides Micro Bevel	4 sides Micro Bevel
Finish	DURASPECT™ DURASPECT™ SILK (Ultra Matt)	DURASPECT™	DURASPECT™
Patented Click System	DropLock-400 (I4F)	DropLock-100 (I4F)	DropLock-100 (I4F)
Mass per Unit Area	8.850 g/m ²	8.850 g/m ²	8.850 g/m ²
Pieces/Carton	24 pieces	22 pieces	4 pieces
Coverage/Carton	2,07 m ²	1,82 m ²	1,72 m ²
Coverage/Pallet	45 Cartons (93,15m ²)	50 Cartons (91,00 m ²)	45 Cartons (77,29 m ²)
Coverage/Container (20')	22 Pallets (2049,30 m ²)	14 Pallets (1274,00m ²)	18 Pallets (1391,22 m ²)
Warranty	Material: 20 years (100%) Labour: 10 years (Pro rata)	Material: 20 years (100%) Labour: 10 years (Pro rata)	Material: 20 years (100%) Labour: 10 years (Pro rata)

EUROPEAN / INTERNATIONAL STANDARDS - CE CERTIFICATION / TESTING			
Description	Standard	Symbol	Results
CE Certification	EN 14041		Refer to Standards Below
Reaction to Fire (and Smoke Production)	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		Bfl - s1 Classification
Formaldehyde Emission	EN 717-1		Class E1
Slip Resistance (Dry)	EN 13893		Class DS

IC55 CONTOURS ISOCORE RIGID CLICK

TECHNICAL DATA SHEET

EUROPEAN / INTERNATIONAL STANDARDS - MANUFACTURING & USAGE (EN 16511)			
Description	Standard	Symbol	Results
Classification (Level of Use)	EN 16511 EN ISO 10874		Commercial - Very Heavy (Class 34) Refer to Standards Below
Wear Resistance IP	ISO 24338 Procedure A		≥7.000 cycles
Impact Resistance (Big Ball)	EN 13329:2006, A1:2008, Annex F		No Visible Damage
Micro-Scratch Resistance [Class]	EN 16094, Method A	N/A	MSR-A2
Castor Chair Resistance	EN ISO 4918		After 25,000 cycles: No Disturbance to the Surface; No Delamination, Cracks, or Disruptions
Effect of Furniture Leg	EN ISO 16581 (Tested with foot type O)		No Visible Damage
Residual Indentation	EN ISO 24343-1		≤0,15mm
Resistance to Staining [Grade, per Group]	EN 438-2 (Group 1 & 3 - Only 10 Minutes)		Groups 1, 2 & 3: Grade 5
Locking Strength	ISO 24334		Long Side ≥ 1,0kN/m Short Side ≥ 3,5kN/m
Dimensional Stability and Curling under influence of Temperature	EN ISO 23999		≤0,15 % ≤ 2mm
Colour Fastness to Light	ISO 105-B02, Method 3		≥Grade 6
Thickness (t)	EN 17539		$\Delta t_{avg} \leq 0,50\text{mm}$ (Versus Nominal) $t_{max} - t_{min} \leq 0,50\text{mm}$
Length (l)	EN 17539		$l \leq 1500\text{mm}$: $\Delta l \leq 0,5\text{mm}$ $l > 1500\text{mm}$: $\Delta l \leq 0,3\text{mm/m}$ (respecto valor nominal)
Width (w)			$\Delta w_{avg} \leq 0,10\text{mm}$ (respecto valor nominal) $w_{max} - w_{min} \leq 0,20\text{mm}$
Squareness (q)			$q_{max} \leq 0,20\text{mm}$
Straightness (s)			$s_{max} \leq 0,30\text{mm/m}$
Flatness (f)	EN 17539	N/A	Maximum Single Values: $f_{w,concave} \leq 0,15\%$, $f_{w,convex} \leq 0,20\%$ $f_{l,concave} \leq 0,50\%$, $f_{l,convex} \leq 1,00\%$
Openings (o)	EN 17539	N/A	Measured from the Surface Between Vertical, Contacting Edges: $o_{avg} \leq 0,15\text{mm}$, $o_{max} \leq 0,20\text{mm}$
Height Difference (h)	EN 17539	N/A	$h_{avg} \leq 0,10\text{mm}$ $h_{max} \leq 0,15\text{mm}$

IC55 CONTOURS ISOCORE RIGID CLICK

TECHNICAL DATA SHEET



EUROPEAN / INTERNATIONAL STANDARDS - AUXILIARY PERFORMANCE & SAFETY			
Description	Standard	Symbol	Results
Slip Resistance (Wet)	DIN EN 16165 : 2023 Annex B	N/A	Grade R10
Slip Resistance (UK)	DIN EN 16165 : 2023 Annex C	N/A	Low Slip Risk (Dry)
Impact Sound Insulation	EN ISO 10140-3 ISO 717-2 EN ISO 140-8		$\Delta L_w = 16$ dB
A-weighted walking sound pressure level	EN 16205:2013		$L_{n,walk, A} = 85$ dB(A)
Thermal Resistance Thermal Conductivity	EN 12664		$R_{23} = 0,074$ (m ² . K)/W $\lambda_{23} = 0,108$ W/m . K
Static Electrical Propensity	EN 1815, Método A		Antistatic Floor Coverings: $\leq 2,0$ kV (Absolute Value)
Product-Content Safety	REACH SVHC	N/A	Not detected
Content of PCP (Pentachlorophenol)	EN 12673:1999		Not detected

Footnotes

1) **Warranty:** Please see full terms and conditions of our warranties at www.aspectaflooring.com

The manufacturing facility is ISO 9001 (Quality Management System), ISO 14001 (Environmental Management System), ISO 45001 (Occupational Health and Safety Management Systems) and SA 8000 (Social Accountability) certified.

Disclaimer: This document represents the current state of knowledge at the time of its publication and instantly supersedes all previous editions. It may be replaced, supplemented or amended at any time and without special notice. Please be sure to check the validity, relevance and content for topicality before issuing a guarantee claim at www.aspectaflooring.com